

# CONSTRUCTION SEALING

## COMPRESSIBLE SEALING GASKET FOR REGULAR JOINTS

### PRACTICAL

It can be applied during construction or during prefabrication for sealing timber-to-timber joints.

### STABLE

Thanks to the solid EPDM mix, it endures over time. It is not affected by chemical attacks.

## COMPOSITION

Extruded compact EPDM



## TECHNICAL DATA

Properties	standard	value	USC conversion
Density	-	0,48 g/cm <sup>3</sup>	0.28 oz/in <sup>3</sup>
Compression deformation 22h +23 °C	EN ISO 815	< 25%	-
Compression deformation 22h +40 °C	EN ISO 815	< 35%	-
Temperature resistance	-	-35 / +100 °C	-31 / +212 °F
Storage temperature <sup>(1)</sup>	-	+5 / +25 °C	+41 / +77 °F
Solvents	-	no	-

<sup>(1)</sup>Store the product in a dry, covered location.  
Waste classification (2014/955/EU): 17 02 03.

## CODES AND DIMENSIONS

CODE	B	s	L	B	s	L	
	[mm]	[mm]	[m]	[in]	[mil]	[ft]	
CONSTRU4625	46	3	25	1.8	118	82	3

## ■ FIELDS OF APPLICATION



## ■ RELATED PRODUCTS



**DOUBLE BAND**  
page 62



**MS SEAL**  
page 120



**HAMMER STAPLER 47**  
page 330



### TESTED RESISTANCE

In Rothoblaas' experimental fire protection project it was tested for an EI value.

### NOISE REDUCTION

The acoustic performance has been tested in the Flanksound Project by Rothoblaas: using it as a wall gasket provides up to 3 dB of noise reduction.